


*In the Claims:*

Please add the following claims:

48. (New) A nanocomposite comprising an organoclay which has been exfoliated into a polymer matrix, the organoclay being the reaction product of a smectite clay with a quaternary ammonium component, wherein the quaternary ammonium component is derived from a process comprising:

mixing at a temperature of about 70 °C a C<sub>12</sub>-C<sub>23</sub> substituted or unsubstituted fatty acid or mixture of fatty acids having an iodine value of from about 3 to about 90, with an ether alkanolamine of the formula:



wherein R, R<sub>1</sub> and R<sub>2</sub> are independently selected from C<sub>2</sub>-C<sub>6</sub> hydroxyalkyl groups, and wherein the molar ratio of the fatty acid to the ether alkanolamine is from about 1.4 to about 2.0,

increasing the temperature of the mixture of the fatty acid and the ether alkanolamine from about 70 °C to a range of from about 170 °C to about 250 °C, wherein the rate of temperature increase is maintained at an average rate of greater than about 0.4 °C per minute to produce a mixture of about 55 wt % of a diester compound and less than about 25 wt % of a triester compound; and


alkylating the produced diester and triester compounds to form the quaternary ammonium component.

49. (New) The nanocomposite of claim 48 wherein the rate of temperature increase is maintained at an average rate greater than about 0.8 °C per minute.
50. (New) The nanocomposite of claim 48 wherein the fatty acid is a substituted or unsubstituted C<sub>16</sub>-C<sub>22</sub> fatty acid having an iodine value of from about 40 to 60.
51. (New) The nanocomposite of claim 48 wherein the fatty acid is a substituted or unsubstituted C<sub>16</sub>-C<sub>22</sub> fatty acid having an iodine value of from about 45 to 55.
52. (New) The nanocomposite of claim 48 wherein the fatty acid is derived from tallow, soy, palm, palm kernel, rape seed, canola, tall oil, lard or mixtures thereof.
53. (New) The nanocomposite of claim 48 wherein the alkanolamine is selected from the group consisting of triethanolamine, propanol diethanolamine, ethanol diisopropanolamine, triisopropanol amine, diethanolisopropanol amine, ethanoldiisobutanolamine, diethanolisobutanolamine and mixtures thereof.
54. (New) The nanocomposite of claim 48 wherein the molar ratio of the fatty acid to the ether alkanolamine is in the range of from about 1.60 to 1.90.
55. (New) The nanocomposite of claim 48 wherein the molar ratio of the fatty acid to the ether alkanolamine is in the range of from about 1.68 to 1.72.

56. (New) The nanocomposite of claim 48, wherein the fatty acid has less than about 10% trans isomer.


57. (New) The nanocomposite of claim 48, wherein the alkylating agent is selected from the group consisting of methyl chloride, benzyl chloride, ethyl chloride, diethyl sulfate, dimethyl carbonate, trimethyl phosphate, dimethyl sulfate or mixtures thereof.

58. (New) A nanocomposite comprising an organoclay which has been exfoliated into a polymer matrix, the organoclay being the reaction product of a smectite clay with a quaternary ammonium component, the quaternary ammonium component comprising a monoester compound of formula (I), a diester compound of formula (II), and a triester compound of formula (III):




Z<sup>-</sup>

I)



Z<sup>-</sup>

II)




Z<sup>-</sup>

III)

wherein X, X' and X'' are the same or different and are selected from straight or branched chain, optionally substituted oxyalkylene or polyoxyalkylene groups having from 2-6 carbon atoms, where the oxyalkylene units number from about 1-10, each R group is individually selected from straight or branched chain, optionally substituted alkyl or alkylene groups having from 11 to 23 carbon atoms, Y is an alkylphenyl group or a straight or branched chain optionally substituted C<sub>1</sub> to C<sub>6</sub> alkyl or alkylene group; and Z<sup>-</sup> represents a halogen or sulfate;

wherein the diester compound comprises greater than about 55 wt.% of the quaternary ammonium component and wherein the triester compound comprises less than about 25 wt.% of the quaternary ammonium component.

59. (New) A nanocomposite comprising an organoclay which has been exfoliated into a polymer matrix, the organoclay being the reaction product of a smectite clay with a quaternary ammonium component, the quaternary ammonium component comprising one or more compounds having the general formula (IV):



E1  
carb. Sub  
F2  
carb.

wherein n is an integer from 1 to 2, R is a C<sub>5</sub> to C<sub>23</sub> straight or branched chain, optionally substituted alkyl or alkylene group, each X can be the same or different and is selected from straight or branched chain, optionally substituted oxyalkylene or polyoxyalkylene groups having from 2-6 carbon atoms; each Q can be the same or different and is selected from a oxyalkylene or polyoxyalkylene group, or straight or branched chain, optionally substituted alkyl, alkylene, alkyl phenyl, hydroxyalkyl, or hydroxyalkylene group, where at least one of said Q groups is a C<sub>2</sub> to C<sub>6</sub> linear or branched chain oxyalkylene or polyoxyalkylene capped with a C<sub>1</sub> to C<sub>6</sub> alkyl, or an alkyl phenyl group; and Z<sup>-</sup> is a halogen or sulfate.

60. (New) The nanocomposite of claim 59, wherein R is a C<sub>7</sub> to C<sub>21</sub>, straight or branched chain, optionally substituted alkyl or alkylene group.

61. (New) The nanocomposite of claim 59, wherein R is a C<sub>11</sub> to C<sub>17</sub>, straight or branched chain, optionally substituted alkyl or alkylene group.

62. (New) The nanocomposite of claim 59, wherein R is a C<sub>13</sub> to C<sub>17</sub>, straight or branched chain, optionally substituted alkyl or alkylene group.


63. (New) The nanocomposite of claim 59, wherein the quaternary ammonium component comprises a diester quaternary ammonium compound and a monoester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises at least about 70% by weight of the quaternary ammonium component.

Sub. 7  
F3

64. (New) A nanocomposite comprising an organoclay which has been exfoliated into a polymer matrix, the organoclay being the reaction product of a smectite clay with a quaternary ammonium component, wherein the quaternary ammonium component is derived from a process comprising:

E1  
cont.  
Sub  
F3  
cont.

reacting a C<sub>11</sub>-C<sub>23</sub> substituted or unsubstituted fatty acid or mixture of fatty acids having an iodine value of from about 20 to about 90, with an ether alkanolamine of the formula:



where R is a C<sub>2</sub>-C<sub>6</sub> alkyl ether, and each of R<sub>1</sub> and R<sub>2</sub> is independently selected from C<sub>2</sub>-C<sub>6</sub> hydroxyalkyl groups, and wherein the molar ratio of the fatty acid to the ether alkanolamine is from about 1.4 to about 2.0; and

alkylating the product of the reaction of the fatty acid with the ether alkanolamine with an alkylating agent to form the quaternary ammonium component.

65. (New) The nanocomposite of claim 64, wherein the fatty acid is a substituted or unsubstituted C<sub>16</sub>-C<sub>22</sub> fatty acid having an iodine value of from about 40 to 60.

66. (New) The nanocomposite of claim 64 wherein the fatty acid is derived from tallow, soy, palm, palm kernel, rape seed, canola, tall oil, lard or mixtures thereof.

67. (New) The nanocomposite of claim 64 wherein the ether alkanolamine is selected from the group consisting of methoxyethyldiethanolamine, methoxypropyldiethanolamine and mixtures thereof.

68. (New) The nanocomposite of claim 64 wherein the molar ratio of fatty acid to ether alkanolamine is in the range of from about 1.60 to about 1.90.

69. (New) The nanocomposite of claim 64 wherein the alkylating agent is selected from the group consisting of methyl chloride, benzyl chloride, ethyl chloride, diethyl sulfate, dimethyl carbonate, trimethyl phosphate, dimethyl sulfate or mixtures thereof.


70. (New) The nanocomposite of claim 64 wherein the alkylating agent is methyl chloride.

71. (New) The nanocomposite of claim 64 wherein the process is conducted in the presence of a solvent.

72. (New) The nanocomposite of claim 64 wherein the process is conducted in the presence of a solvent, wherein the solvent is selected from the group consisting of C<sub>1</sub>-C<sub>6</sub> alcohols, glycols, fatty acid, mono-, di-, or tri-glycerides, and mixtures thereof.

73. (New) An organoclay comprising the reaction product of a smectite clay with a quaternary ammonium component, wherein the quaternary ammonium component is derived from a process comprising:

mixing at a temperature of about 70 °C a C<sub>12</sub>-C<sub>23</sub> substituted or unsubstituted fatty acid or mixture of fatty acids having an iodine value of from about 3 to about 90, with an ether alkanolamine of the formula:



wherein R, R<sub>1</sub> and R<sub>2</sub> are independently selected from C<sub>2</sub>-C<sub>6</sub> hydroxyalkyl groups, and wherein the molar ratio of the fatty acid to the ether alkanolamine is from about 1.4 to about 2.0,

increasing the temperature of the mixture of the fatty acid and the ether alkanolamine from about 70 °C to a range of from about 170 °C to about 250 °C, wherein the rate of temperature increase is maintained at an average rate of greater than about 0.4 °C per minute to produce a mixture of about 55 wt % of a diester compound and less than about 25 wt % of a triester compound; and

alkylating the produced diester and triester compounds to form the quaternary ammonium component.

74. (New) The organoclay of claim 73 wherein the rate of temperature increase is maintained at an average rate greater than about 0.8 °C per minute.

75. (New) The organoclay of claim 73 wherein the fatty acid is a substituted or unsubstituted C<sub>16</sub>-C<sub>22</sub> fatty acid having an iodine value of from about 40 to 60.

76. (New) The organoclay of claim 73 wherein the fatty acid is a substituted or unsubstituted C<sub>16</sub>-C<sub>22</sub> fatty acid having an iodine value of from about 45 to 55.



77. (New) The organoclay of claim 73 wherein the fatty acid is derived from tallow, soy, palm, palm kernel, rape seed, canola, tall oil, lard or mixtures thereof.

78. (New) The organoclay of claim 73 wherein the alkanolamine is selected from the group consisting of triethanolamine, propanol diethanolamine, ethanol diisopropanolamine, triisopropanol amine, diethanolisopropanol amine, ethanoldiisobutanolamine, diethanolisobutanolamine and mixtures thereof.


79. (New) The organoclay of claim 73 wherein the molar ratio of the fatty acid to the ether alkanolamine is in the range of from about 1.60 to 1.90.

80. (New) The organoclay of claim 73 wherein the molar ratio of the fatty acid to the ether alkanolamine is in the range of from about 1.68 to 1.72.

81. (New) The organoclay of claim 73, wherein the fatty acid has less than about 10% trans isomer.


82. (New) The organoclay of claim 73, wherein the alkylating agent is selected from the group consisting of methyl chloride, benzyl chloride, ethyl chloride, diethyl sulfate, dimethyl carbonate, trimethyl phosphate, dimethyl sulfate or mixtures thereof.

83. (New) An organoclay comprising a reaction product of a smectite clay with a quaternary ammonium component, the quaternary ammonium component comprising a monoester compound of formula (I), a diester compound of formula (II), and a triester compound of formula (III):




Z<sup>-</sup>

I)



Z<sup>-</sup>

II)



Z<sup>-</sup>


III)

wherein X, X' and X'' are the same or different and are selected from straight or branched chain, optionally substituted oxyalkylene or polyoxyalkylene groups having from 2-6 carbon atoms, where the oxyalkylene units number from about 1-10, each R group is individually selected from straight or branched chain, optionally substituted alkyl or alkylene groups having from 11 to 23 carbon atoms, Y is an alkylphenyl group or a straight or branched chain optionally substituted C<sub>1</sub> to C<sub>6</sub> alkyl or alkylene group; and Z<sup>-</sup> represents a halogen or sulfate;

El  
cont.  
Sub  
FY  
cont.

wherein the diester compound comprises greater than about 55 wt.% of the quaternary ammonium component and wherein the triester compound comprises less than about 25 wt.% of the quaternary ammonium component.

84. (New) An organoclay comprising the reaction product of a smectite clay with a quaternary ammonium component, the quaternary ammonium component comprising one or more compounds having the general formula (IV):



wherein n is an integer from 1 to 2, R is a C<sub>5</sub> to C<sub>23</sub> straight or branched chain, optionally substituted alkyl or alkylene group, each X can be the same or different and is selected from straight or branched chain, optionally substituted oxyalkylene or polyoxyalkylene groups having from 2-6 carbon atoms; each Q can be the same or different and is selected from a oxyalkylene or polyoxyalkylene group, or straight or branched chain, optionally substituted alkyl, alkylene, alkyl phenyl, hydroxyalkyl, or hydroxyalkylene group, where at least one of said Q groups is a C<sub>2</sub> to C<sub>6</sub> linear or branched chain oxyalkylene or polyoxyalkylene capped with a C<sub>1</sub> to C<sub>6</sub> alkyl, or an alkyl phenyl group; and Z<sup>-</sup> is a halogen or sulfate.

85. (New) The organoclay of claim 84, wherein R is a C<sub>7</sub> to C<sub>21</sub>, straight or branched chain, optionally substituted alkyl or alkylene group.


86. (New) The organoclay of claim 84, wherein R is a C<sub>11</sub> to C<sub>17</sub>, straight or branched chain, optionally substituted alkyl or alkylene group.

87. (New) The organoclay of claim 84, wherein ~~R~~ is a C<sub>13</sub> to C<sub>17</sub>, straight or branched chain, optionally substituted alkyl or alkylene group

88. (New) The organoclay of claim 84, wherein the quaternary ammonium component comprises a diester quaternary ammonium compound and a monoester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises at least about 70% by weight of the quaternary ammonium component.

89. (New) An organoclay comprising a reaction product of a smectite clay with a quaternary ammonium component, wherein the quaternary ammonium component is derived from a process comprising:

reacting a C<sub>11</sub>-C<sub>23</sub> substituted or unsubstituted fatty acid or mixture of fatty acids having an iodine value of from about 20 to about 90, with an ether alkanolamine of the formula:



where R is a C<sub>2</sub>-C<sub>6</sub> alkyl ether, and each of R<sub>1</sub> and R<sub>2</sub> is independently selected from C<sub>2</sub>-C<sub>6</sub> hydroxyalkyl groups, and wherein the molar ratio of the fatty acid to the ether alkanolamine is from about 1.4 to about 2.0; and

alkylating the product of the reaction of the fatty acid with the ether alkanolamine with an alkylating agent to form the quaternary ammonium component.

E1  
const.

Sub  
FS  
const.

90. (New) The organoclay of claim 89, wherein the fatty acid is a substituted or unsubstituted C<sub>16</sub>-C<sub>22</sub> fatty acid having an iodine value of from about 40 to 60.

91. (New) The organoclay of claim 89 wherein the fatty acid is derived from tallow, soy, palm, palm kernel, rape seed, canola, tall oil, lard or mixtures thereof.

92. (New) The organoclay of claim 89 wherein the ether alkanolamine is selected from the group consisting of methoxyethyldiethanolamine, methoxypropyldiethanolamine and mixtures thereof.

93. (New) The organoclay of claim 89 wherein the molar ratio of fatty acid to ether alkanolamine is in the range of from about 1.60 to about 1.90.

94. (New) The organoclay of claim 89 wherein the alkylating agent is selected from the group consisting of methyl chloride, benzyl chloride, ethyl chloride, diethyl sulfate, dimethyl carbonate, trimethyl phosphate, dimethyl sulfate or mixtures thereof.

95. (New) The organoclay of claim 89 wherein the alkylating agent is methyl chloride.

96. (New) The organoclay of claim 89 wherein the process is conducted in the presence of a solvent.

97. (New) The organoclay of claim 89 wherein the process is conducted in the presence of a solvent, wherein the solvent is selected from the group consisting of C<sub>1</sub>-C<sub>6</sub> alcohols, glycols, fatty acid, mono-, di-, or tri-glycerides, and mixtures thereof.

96. (New) The nanocomposite of claim 1, wherein the additional quaternary ammonium

compound is a triester quaternary ammonium compound and wherein the triester quaternary ammonium compound comprises less than about 25 wt% of the quaternary onium compound mixture.

91  
96  
cont.

97. (New) The nanocomposite of claim 1, wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 20 to about 90.

98. (New) The nanocomposite of claim 1, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 60 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 20 wt% of the quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 30 to about 70.

99. (New) The nanocomposite of claim 1, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 62 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 17 wt% of the quaternary onium mixture, and ~~the IV~~ wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 40 to about 60.

100. (New) The nanocomposite of claim 1, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 62 wt% of the quaternary onium mixture,

41  
cont.  
the triester quaternary ammonium compound comprises less than about 17 wt% of the quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 45 to about 58.

101. (New) The organoclay composition of claim 12, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound and wherein the triester quaternary ammonium compound comprises less than about 25 wt% of the quaternary onium compound mixture.

102. (New) The organoclay composition of claim 10, wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 20 to about 90.

103. (New) The organoclay composition of claim 10, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 60 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 20 wt% of the quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 30 to about 70.

104. (New) The organoclay composition of claim 10, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 62 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 17 wt% of the

quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 40 to about 60.

96  
Cont: 105. (New) The organoclay composition of claim 10, wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 45 to about 58.

106. (New) The method of claim 31, wherein the diester quaternary ammonium compound is present as greater than 55 wt% of the quaternary onium compound mixture.

107. (New) The method of claim 31, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound and wherein the triester quaternary ammonium compound comprises less than about 25 wt% of the quaternary onium compound mixture.

108. (New) The method of claim 31, wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 20 to about 90.

109. (New) The method of claim 31, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 60 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 20 wt% of the quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 30 to about 70.



81  
cont

110. (New) The method of claim 31, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 62 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 17 wt% of the quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 40 to about 60.


111. (New) The method of claim 31, wherein the additional quaternary ammonium compound is a triester quaternary ammonium compound, and wherein the diester quaternary ammonium compound comprises greater than about 62 wt% of the quaternary onium mixture, the triester quaternary ammonium compound comprises less than about 17 wt% of the quaternary onium mixture, and wherein the fatty acids corresponding to the esters in the diester quaternary ammonium compound and the additional quaternary ammonium compound have a degree of unsaturation such that the iodine value is from about 45 to about 58.

---

Powell, et al.  
09/422,154

Applicant has enclosed a fee authorization including an authorization for \$1824 for the excess claims fees. If any other fees are inadvertently omitted or if any additional fees are required or have been overpaid, please appropriately charge or credit those fees to Conley, Rose & Tayon, P.C. Deposit Account Number 50-1505/5628-00403/EBM

Respectfully submitted,

A large, stylized handwritten signature in black ink, likely belonging to Eric B. Meyertons, is written over the "Respectfully submitted," text.

Eric B. Meyertons  
Reg. No. 34,876  
Attorney for Applicant

CONLEY, ROSE & TAYON, P.C.  
P.O. BOX 398  
AUSTIN, TX 78767-0398  
(512) 703-1254 (voice)  
(512) 703-1250 (facsimile)

Date: 5/13/07